

# Wieland-Z31/41/48

CuZn40Pb2 | Machining / hot-stamping brass

## Material designation

EN	CuZn40Pb2 CW617N
UNS	C38000

## Chemical composition\*

Cu	58 %
Pb**	2 %
Zn	balance

\*Reference values in % by weight  
\*\*for Z41/Z48 max. 2.2 %

## Physical properties\*

Electrical conductivity	MS/m	14.9
	%IACS	25
Thermal conductivity	W/(m·K)	113
Thermal expansion coefficient (0–300 °C)	10 <sup>-6</sup> /K	21.1
Density	g/cm <sup>3</sup>	8.43
Modulus of elasticity	GPa	96

\*Reference values at room temperature

## Corrosion resistance

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline compounds. Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress. Dezincification in warm, acidic waters should also be taken into consideration.

## Product standards

Rod	EN 12164 EN 12165
Wire	EN 12166
Section	EN 12167
Hollow rod	EN 12168
Tube	EN 12449

## Material properties and typical applications

Wieland-Z31/Z41/Z48 are the reference materials for hot working. The mean lead content provides good machinability of the drop-forged part. Because of its composition the alloy is also suited for the production of drawn, complex profile shapes.

Wieland-Z48 has been specially optimised for hot working.

Wieland-Z41 has been specially optimised for the manufacture of rods for machining purposes which are supplied in the proven W5000 quality.

Both types Wieland-Z41 and Wieland-Z48 are hygienically suitable for contact with drinking water according to the UBA (Federal Environment Agency) list.

Wieland-Z31 can be used if the material is not required to comply with drinking water requirements.

## Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

## Fabrication properties

### Forming

Machinability (CuZn39Pb3 = 100 %)	95 %
Capacity for being cold worked	poor
Capacity for being hot worked	excellent

### Surface treatment

Polishing	
mechanical	good
electrolytic	poor
Electroplating	excellent

### Joining

Resistance welding (butt weld)	fair
Inert gas shielded arc welding	poor
Gas welding	poor
Hard soldering	fair
Soft soldering	excellent

### Heat treatment

Melting range	880–895 °C
Hot working	650–800 °C
Soft annealing	450–600 °C 1–3 h
Thermal stress relieving	200–300 °C 1–3 h

## Trademarks



# Wieland-PSR

Further information is provided in the brochures on W5000 and Wieland-PSR.

# Wieland-Z31/41/48

CuZn40Pb2 | Machining / hot-stamping brass

## Mechanical properties according to EN

Round rods/polygonal rods												acc. to EN 12164	
Temper	Diameter		Width across flats		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness		
	mm		mm		MPa	MPa		A100	A11.3	A	HB		
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
M	all		all		as manufactured – without specified mechanical properties								
R360	6	80	5	60	360	–	350	–	15	20	–	–	
H090	6	80	5	60	–	–	–	–	–	–	90	125	
R430	2	60	2	40	430	–	220	–	6	8	10	–	–
H110	2	60	2	40	–	–	–	–	–	–	110	160	
R500	2	14	2	10	500	–	350	–	–	3	5	–	–
H135	2	14	2	10	–	–	–	–	–	–	135	–	

Rectangular rods												acc. to EN 12167	
Temper	Thickness			Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm			MPa	MPa		A100	A11.3	A	HB			
	from	to		min.	min.	max.	min.	min.	min.	min.	max.		
M	all			as manufactured – without specified mechanical properties									
R360	6	40		360	–	320	–	15	20	–	–		
H090	6	40		–	–	–	–	–	–	90	125		
R430	3	20		430	–	220	–	6	8	10	–	–	
H110	3	20		–	–	–	–	–	–	110	160		
R500	3	10		500	–	350	–	2	5	8	–	–	
H135	3	10		–	–	–	–	–	–	135	–		

Tubes												acc. to EN 12449	
Temper	Wall thickness		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %	Hardness						
	mm		MPa	MPa		A	HV		HB				
	from	to	min.	min.	max.		min.	max.	min.	max.			
M	–	20	as manufactured – without specified mechanical properties										
R360	–	10	360	–	250	25	–	–	–	–	–		
H085	–	10	–	–	–	–	85	120	80	115	–		
R430	–	10	430	–	250	12	–	–	–	–	–		
H115	–	10	–	–	–	–	115	150	110	145	–		
R500	–	5	500	–	370	8	–	–	–	–	–		
H140	–	5	–	–	–	–	140	–	135	–	–		

Round wires												acc. to EN 12166	
Temper	Diameter		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Härte				
	mm		MPa	MPa		A100	A11.3	A	HB				
	from	to	min.	min.	max.	min.	min.	min.	min.	max.			
M	all		as manufactured – without specified mechanical properties										
R360	6	20	360	–	320	–	15	20	–	–			
H095	6	20	–	–	–	–	–	–	95	130			
R430	0.5	14	430	–	220	–	6	8	10	–	–		
H115	1.5	14	–	–	–	–	–	–	115	170			
R500	0.5	8	500	–	350	–	2	5	–	–			
H145	1.5	8	–	–	–	–	–	–	145	–			

Wieland-Werke AG | Graf-Arco-Straße 36 | 89079 Ulm | Germany  
 info@wieland.com | wieland.com

This printed matter is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The product characteristics are not guaranteed and do not replace our experts' advice.